



耐熱級 ASA, KIBILAC[®] PW-978B

March 22, 2007 VIW

材料特性

特性(Properties)	測試方法(Test Method)	測試條件(Test Condition)	單位(Unit)	PW-978B
引張強度 Tensile Strength	ASTM D638	1/8", 6 mm/min	Kg/cm ² (lb/in ²)	450(6380)
彎曲強度 Flexural Strength	ASTM D790	1/4", 2.8 mm/min	Kg/cm ² (lb/in ²)	600(8520)
IZOD 衝擊強度 Izod Impact Strength	ASTM D256(Notched)	1/4", 23 1/8", 23	Kg-cm/cm(ft-lb/in) Kg-cm/cm(ft-lb/in)	10(1.9) 15(2.8)
流動係數 Melt Flow Index	ASTM D1238	220 , 10Kg	g/10min	13
比重 Specific Gravity	ASTM D792	23	-	1.07
光澤度 Gloss	ASTM D523	-	-	95
軟化點 Vicat Softening Temp	ASTM D1525	1/8", 50 /hr	()	113(235)
熱變形溫度 H.D.T Annealed Unannealed	ASTM D648	1/4", 120 /hr	()	103(217) 93(199)

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 06-2665000, 06-2663000