

# CHIMEI

奇美實業股份有限公司  
CHI MEI CORPORATION

台南縣仁德鄉三甲村59-1號  
TEL: 886-6-266-5000 FAX: 886-6-266-5555~7

## 高光澤級 PS, POLYREX<sup>®</sup> PH-888G

January 10, 2008 VIW

### 材料特性

特性(Properties)	測試方法(Test Method)	測試條件(Test Condition)	單位(Unit)	PH-888G
引張強度 Tensile Strength	ASTM D638	1/8", 6 mm/min	Kg/cm <sup>2</sup> (lb/in <sup>2</sup> )	320(4540)
延伸率 Tensile Elongation	ASTM D638	1/8", 6 mm/min	%	30
彎曲強度 Flexural Strength	ASTM D790	1/4", 2.8 mm/min	Kg/cm <sup>2</sup> (lb/in <sup>2</sup> )	540(7670)
彎曲彈性率 Flexural Modulus	ASTM D790	1/4", 2.8 mm/min	Kg/cm <sup>2</sup> (lb/in <sup>2</sup> )	21000(300000)
IZOD 衝擊強度 Izod Impact Strength	ASTM D256(Notched)	1/4", 23 1/8", 23	Kg-cm/cm(ft-lb/in) Kg-cm/cm(ft-lb/in)	8.5(1.56) 9.5(1.74)
流動係數 Melt Flow Index	ASTM D1238	200 , 5Kg	g/10min	4.0
硬度 Hardness	ASTM D785	1/4"	L Scale	85
比重 Specific Gravity	ASTM D792	23	-	1.05
軟化點 Vicat Softening Temp.	ASTM D1525	1/8", 50 /hr	( )	102(215)
熱變形溫度 Heat Distortion Temp.	ASTM D648	1/4", 120 /hr	( )	85(185)
燃燒率 Flammability	UL 94	-	-	1/16"HB

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 06-2665000, 06-2663000