



泛用級 TPE, KIBITON[®] PB-585

VIW

材料特性

特性(Properties)	測試方法(Test Method)	測試條件(Test Condition)	單位(Unit)	PB-585
丁二烯/苯乙烯比例 BD/SM	ASTM D1416	-	%	68/32
揮發份 Volatile matter	ASTM D1416	-	wt%	0.6
灰份 Ash Content	ASTM D1416	-	wt%	1.0
加工含油量 Oil Content	ASTM D1416	-	phr	45
流動係數 Melt Flow Index	ASTM D1238	200°C , 5Kg	g/10min	10.0
流動係數 Melt Flow Index	ASTM D1238	190°C , 5Kg	g/10min	7.0
硬度 Hardness	ASTM D2240	-	Shore A	45
比重 Specific Gravity	ASTM D792	23°C	-	0.94
外觀 Appearance	-	-	-	發泡顆粒 Foam Pellet
包裝 Bale Weight	-	-	Kg	20

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 06-2665000, 06-2663000