



CHI MEI CORPORATION

59-1 SAN CHIA, JEN TE, TAINAN COUNTY, TAIWAN R.O.C. TEL: 886-6-266-5000, FAX: 886-6-266-5555-7

泛用級 TPE, KIBITON[®] PB-5301

December 20, 2006 VIW

材料特性

特性(Properties)	測試方法(Test Method)	測試條件(Test Condition)	單位(Unit)	PB-5301
丁二烯/苯乙烯比例 BD/SM	ASTM D1416	-	%	69/31
揮發份 Volatile matter	ASTM D1416	-	wt%	0.4
灰份 Ash Content	ASTM D1416	-	wt%	1
加工含油量 Oil Content	ASTM D1416	-	phr	0
流動係數 Melt Flow Index	ASTM D1238	200 ,5Kg	g/10min	<0.5
流動係數 Melt Flow Index	ASTM D1238	190 ,5Kg	g/10min	<0.5
硬度 Hardness	ASTM D2240	-	Shore A	74
比重 Specific Gravity	ASTM D792	23	-	0.94
外觀 Appearance	-	-	-	顆粒 Pellet
包裝 Bale Weight	-	-	Kg	15

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 06-2665000, 06-2663000